

VILAS 237

**Client's name** : SAINT-GOBAIN VIETNAM LTD  
*Tên khách hàng* : CÔNG TY TNHH SAINT-GOBAIN VIỆT NAM

**Client's address** : LOT C20B, STREET 11, HIEP PHUOC INDUSTRIAL PARK, HIEP PHUOC VILLAGE, NHA BE DISTRICT, HCM CITY  
*Địa chỉ* : LÔ C20B, ĐƯỜNG 11, KHU CÔNG NGHIỆP HIỆP PHƯỚC, XÃ HIỆP PHƯỚC, HUYỆN NHÀ BÈ, TP.HCM

The following sample(s) was/were submitted and identified by the client as:

*Các thông tin nhận dạng mẫu do khách hàng cung cấp:*

**Name of sample / Tên mẫu** : MẪU CHÓNG THẨM WEBERDRY PU


**Quantity / Số lượng mẫu** : 01 sample / mẫu

**Date of receiving / Ngày nhận mẫu** : 01-Aug-2023

**Time of testing / Thời gian thử nghiệm** : From / từ 02-Aug-2023 to / đến 07-Sep-2023

**Test result / Kết quả thử nghiệm** : See next page(s) / Xem trang sau

Signed for and on behalf of  
**SGS Vietnam LTD**

Thay mặt công ty  
  
 SGS Vietnam Ltd

**Luu Van Trung**  
 Laboratory Supervisor  
 Industrial Services

124598

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Characteristic <i>Tên chỉ tiêu</i>	Unit <i>Đơn vị</i>	Test method <i>Phương pháp thử nghiệm</i>	Test result <i>Kết quả thử nghiệm</i>
1. Pull-off adhesion strength of coatings on concrete substrate at 28 days (*) / Cường độ bám dính trên nền bê tông ở 28 ngày	MPa	ASTM D7234 - 21	1.17
2. Crack bridging ability (*) <i>Khả năng tạo cầu vết nứt</i>	mm	BS EN 14891 : 2017	6.38

**Note / Ghi chú:**

- (\*) The test was accredited ISO 17025:2017 by VILAS / Chỉ tiêu được công nhận ISO 17025:2017 bởi VILAS.  
 ILAC : International Laboratory Accreditation / Tổ chức hợp tác công nhận Phòng thử nghiệm quốc tế.  
 MRA : Mutual Recognition Arrangement / Thỏa ước thừa nhận lẫn nhau.  
 ILAC-MRA-VILAS : VILAS is the full member and signatory of Mutual Recognition Arrangement with International Laboratory Accreditation / VILAS là thành viên đầy đủ và ký thỏa ước thừa nhận lẫn nhau với tổ chức công nhận phòng thử nghiệm quốc tế.
- Rate of use specified by the client: 2 kg/m<sup>2</sup> (apply 2 coats) / Định mức sử dụng do khách hàng chỉ định: 2 kg/m<sup>2</sup> (quét 2 lớp).

\*\*\* END OF THE REPORT \*\*\*

124599

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.