

Client's name : SAINT-GOBAIN VIETNAM LTD
Tên khách hàng : CÔNG TY TNHH SAINT-GOBAIN VIỆT NAM

Client's address : LOT C20B, STREET 11, HIEP PHUOC INDUSTRIAL PARK, HIEP PHUOC VILLAGE, NHA BE DISTRICT, HCM CITY
Địa chỉ : LÔ C20B, ĐƯỜNG 11, KHU CÔNG NGHIỆP HIỆP PHƯỚC, XÃ HIỆP PHƯỚC, HUYỆN NHÀ BÈ, TP.HCM

The following sample(s) was/were submitted and identified by the client as:

Các thông tin nhận dạng mẫu do khách hàng cung cấp:

Name of sample / Tên mẫu : Màng chống thấm Weberproof TPO - Trải trước
Quantity / Số lượng mẫu : 01 sample / mẫu
Date of receiving / Ngày nhận mẫu : 25-Sep-2023
Time of testing / Thời gian thử nghiệm : From / từ 25-Sep-2023 to / đến 27-Sep-2023
Test result / Kết quả thử nghiệm : See next page(s) / Xem trang sau



SGS authenticate the photos on original report only / SGS chỉ xác thực các hình ảnh trong báo cáo chính thức

Signed for and on behalf of
SGS Vietnam LTD

Thay mặt công ty

SGS SGS Vietnam Ltd

Luu Van Trung
Laboratory Supervisor
Industrial Services

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Characteristic <i>Tên chỉ tiêu</i>	Unit <i>Đơn vị</i>	Test method <i>Phương pháp thử nghiệm</i>	Test result <i>Kết quả thử nghiệm</i>
1. Thickness of sample with sand <i>Chiều dày mẫu có cát</i>	mm	As the client's request <i>Theo yêu cầu khách hàng</i>	1.87
2. Thickness of sample without sand <i>Chiều dày mẫu không có cát</i>	mm	As the client's request <i>Theo yêu cầu khách hàng</i>	1.22
3. Tensile strength (*) (a) <i>Độ bền kéo</i>			
• Longitudinal direction <i>Hướng dọc</i>	MPa	ASTM D412 - 16 (Reapproved 2021)	19.5
• Transverse direction <i>Hướng ngang</i>	MPa		20.1
4. Elongation at break (*) (a) <i>Độ giãn dài khi đứt</i>			
• Longitudinal direction <i>Hướng dọc</i>	%	ASTM D412 - 16 (Reapproved 2021)	733
• Transverse direction <i>Hướng ngang</i>	%		854

Note / Ghi chú:

- (*) The test was accredited ISO 17025:2017 by VILAS / *Chỉ tiêu được công nhận ISO 17025:2017 bởi VILAS.*
 ILAC: International Laboratory Accreditation / *Tổ chức hợp tác công nhận Phòng thử nghiệm quốc tế.*
 MRA: Mutual Recognition Arrangement / *Thỏa ước thừa nhận lẫn nhau.*
 ILAC-MRA -VILAS: VILAS is the full member and signatory of Mutual Recognition Arrangement with International Laboratory Accreditation / *VILAS là thành viên đầy đủ và ký thỏa ước thừa nhận lẫn nhau với tổ chức công nhận phòng thử nghiệm quốc tế.*
- Lab environmental conditions / *Điều kiện môi trường phòng thử nghiệm* : (23 ± 2) °C, (50 ± 10) %RH.
- (a) Test speed : 500 mm/min / *Tốc độ thử : 500 mm/phút.*
 Gauge length / *Chiều dài tính toán ban đầu* : 25 mm.
 Testing on the part without sand / *Thử nghiệm trên phần không có cát.*

*** END OF THE REPORT ***

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.